

AMENDMENT

Claims 1-14 (cancelled)

Claim 15 (previously amended) A coextrusion blown film comprising at least one structural layer, at least one adhesive layer and optionally at least one barrier layer, the blown film obtained by a film fabrication process wherein the process time is 12 seconds or less, and wherein the adhesive composition comprises:

a) a polyethylene selected from the group consisting of conventional-HDPE, conventional-MDPE, conventional-LLDPE, conventional-VLDPE, LDPE, and a blend of any of these five,

b) from 5 to 35 weight percent, based on the total weight of a) plus b) plus c), of an acid-grafted substantially linear polyethylene, c) optionally up to 30 weight percent of a hydrocarbon elastomer, the acid grafting agent being an unsaturated carboxylic acid or its derivative, and the level of grafting being such that the total amount of grafting agent in the total composition a) plus b) plus c) is from 0.01 to 3 weight percent.

Claims 16-22 (cancelled)

Claim 23 (previously added) The blown film of Claim 15 wherein the adhesive composition comprises from about 5 to about 30 weight percent, based on the total weight of (a) plus (b) plus (c), of an acid-grafted substantially linear polyethylene.

Claim 24 (previously added) The blown film of Claim 23 wherein the adhesive composition comprises from about 8 to about 25 weight percent of (a) plus (b) plus (c).

Claim 25 (previously added) The blown film of Claim 24 wherein component (c) is present in an amount of from about 1 to about 25 weight percent.

Claim 26 (previously added) The blown film of Claim 25 wherein component (c) is present in an amount of from about 3 to about 25 weight percent.

Claim 27 (previously added) The blown film of Claim 26 wherein component (c) is present in an amount of from about 5 to about 25.

Claim 28 (previously added) The blown film of Claim 15 wherein the structural layer is selected from the group of ethylene homopolymers, ethylene copolymers and ethylene ionomers.

Claim 29 (currently amended) The blown film of Claim 15 wherein at least one structural layer is selected from the group consisting of propylene homopolymers ~~home~~ and copolymers, ~~and nylon polymers.~~

Claim 30 (previously added) The blown film of Claim 15 wherein at least one layer is a barrier layer.

Claim 31 (previously added) The blown film of Claim 30 wherein the barrier layer is an ethylene vinyl alcohol polymer or a nylon polymer or both.

Claim 32 (previously added) The blown film of Claim 15 wherein the adhesive component b) is less than 30 weight percent of the total adhesive composition, and the amount of grafting agent is from about 0.05 to about 0.25 weight percent of the total composition a) plus b) plus c).

Claim 33 (previously added) The blown film of Claim 15 wherein the adhesive component b) is melt-blended prior to coextrusion.

Claim 34 (previously added) The blown film of Claim 15 wherein the adhesive component b) is dry-blended and melt mixed during co-extrusion.